


Ì

C

ASTENER

7/8 CORRUGATED



The **7/8 Corrugated** is commonly used for a wide variety of architectural, agricultural, commercial and industrial applications. **7/8 Corrugated** is a structural panel and an exposed fastener panel that can be used for wall applications.

7/8 Corrugated is designed for industrial, commercial, and steel-frame building applications.

Features

- Finishes: Standard: Painted, Bare Galvanized and Galvalume®
- Corrosion Protection: AZ55 per ASTM A 792 for unpainted Galvalume® AZ50 per ASTM A 792 for painted Galvalume®
 - G90 per ASTM A 653 for Galvanized
- Gauges: 26 ga and 24 ga standard; 22 ga and 20 ga optional
- 32" panel coverage, alternate coverages are available, 7/8" rib height
- Panel Length: Minimum: 3'; Maximum: 45' recommended
- Applies over open framing or solid substrate
- · Panels can be installed horizontally or vertically

Testing and Approvals

- UL 2218 Impact Resistance Class 4
- UL 263 Fire Resistance Rating per assembly
- ASTM E 283 Air Leakage 0.004 cfm/ft2 at 6.24 psf *
- ASTM E 331 Water Penetration none at 12 psf*
- ASTM E 1592 Structural Performance
- ASTM E 330 Structural Performance
- 2017 FBC Approval FL9482.1
- * uses Double Bead Tape Sealant and Stitch Screws 1' oc in Side Lap



AIA 🖉

QUALITY METALS © ALL RIGHTS RESERVED 2018



San Antonio • 2707 Castroville Rd • San Antonio, TX 78237 • (210) 227-7276 • Fax (210) 227-0329 McAllen • 2221 Austin Ave • McAllen, TX 78501 • (956) 627-2966 • Fax (956) 627-0918 Dallas • 2515 Willowbrook Rd 100 • Dallas, TX 75220 • (972) 331 6800 • Fax (972) 331 6803 Houston • 6460 Langfield Road • Houston, TX 77092 • (713) 944-4480 • Fax (713) 944-4430

7/8 CORRUGATED



SECTION PROPERTIES									ALLOWABLE UNIFORM LOADS, PSF FOR VARIOUS FASTENER SPACINGS											
GA	WIDTH IN	YIELD KSI	WEIGHT PSF	TOP IN COMPRESSION		BOTTOM IN COMPRESSION		INWARD LOAD					OUTWARD LOAD							
				IN ⁴ /FT	IN ³ /FT	IN ⁴ /FT	IN ³ /FT	2'	3'	4'	5'	6'	7'	2'	3'	4'	5 '	6'	7'	
26	34.67	50	0.94	0.0256	0.0576	0.0256	0.0576	322	147	66	34	20	12	322	147	66	34	20	12	
24	34.67	50	1.22	0.0312	0.0739	0.0312	0.0739	412	188	80	41	24	15	412	188	80	41	24	15	
22	34.67	50	1.60	0.0415	0.0950	0.0415	0.0950	530	241	107	55	32	20	530	241	107	55	32	20	
20	34.67	33	1.95	0.0485	0.1139	0.0485	0.1139	419	191	108	64	37	23	419	191	108	64	37	23	

1. Theoretical section properties have been calculated per AISI 2012 'North American Specification for the Design of Cold-Formed Steel Structural Members'. Ixx and Sxx are effective section properties for deflection and bending.


2. Allowable load is calculated in accordance with AISI 2012 specifications considering bending, shear, combined bending and shear and deflection. Allowable load considers the 3 or more equal spans condition. Allowable load does not address web crippling, fasteners, support material or load testing. Panel weight is not considered.

3. Deflection consideration is limited by a maximum deflection ratio of L/180 of span.

4. Allowable loads do not include a 1/3 stress increase for wind.



Descriptions and specifications contained herein were in effect at the time this publication was approved for printing. In a continuing effort to refine and improve products, Quality Metals reserves the right to discontinue products at any time or change specifications and/or designs without incurring obligation. To ensure you have the latest information available, please inquire or visit our website at www.saqualitymetals.com. Application details are for illustration purposes only and may not be appropriate for all environmental conditions, building designs or panel profiles. Projects should be designed to confirm to applicable building codes, regulations and accepted industry practices. If there is a conflict between this manual and project erection drawings, the erection drawings will take precedence.





San Antonio • 2707 Castroville Rd • San Antonio, TX 78237 • (210) 227-7276 • Fax (210) 227-0329 McAllen • 2221 Austin Ave • McAllen, TX 78501 • (956) 627-2966 • Fax (956) 627-0918 Dallas • 2515 Willowbrook Rd 100 • Dallas, TX 75220 • (972) 331 6800 • Fax (972) 331 6803 Houston • 6460 Langfield Road • Houston, TX 77092 • (713) 944-4480 • Fax (713) 944-4430